

WHEN YOU NEED TO BE SURE

GRANULATED BLAST FURNACE SLAG



www.sopelinc.com



info@jsopelinc.com



+82-10-3422-2885



202HO 101 DONG HANSHIN VILLAT 258-29 HOWON DONG UIJEONG BU SHI GYEONGGI DO SOUTH KOREA.



GRANULATED BLAST FURNACE SLAG SPECIFICATION

NO	SAMPLE	ELEMENTS	ALKALIES	AL ₂ O ₃	FE ₂ O ₃	MGO	MOISTURE	MNO	S	SIO ₂	TIO ₂
1	1	%	0.46	2.91	0.27	2.6	8.59	0.16	0.3	42.22	0.13



WHEN YOU NEED TO BE SURE

GROUND GRANULATED FURNACE SLAG



www.sopelinc.com



info@jsopelinc.com



+82-10-3422-2885



202HO 101 DONG HANSHIN VILLAT 258-29 HOWON DONG UIJEONG BU SHI GYEONGGI DO SOUTH KOREA.



SOPEL INC. © ALL RIGHTS RESERVED SINCE 2005.®

+82-10-3422-2885

info@sopelinc.com

Jee Woon Kim Mr.

GROUND GRANULATED FURNACE SLAG SPECIFICATION

NO	SAMPLE	ELEMENTS	AL ₂ O ₃	BASICITY 1	BASICITY 2	CAO	CR ₂ O ₃	FE ₂ O ₃	MGO	MNO	P ₂ O ₅	SIO ₂	TOTAL FE	TIO ₂	V ₂ O ₅
1	1	%	5.25	1.75	1.61	29.46	0.28	34.08	11.86	1.14	0.37	18.3	23.83	0.9	0.68
2	2	%	6.11	1.64	1.59	29.35	0.28	36.21	11.14	0.92	0.39	18.47	25.32	1.06	0.78

ADDITIONAL INFORMATION.

NO	ARTICLE	PERCENTAGE	NO	ARTICLE	PERCENTAGE
1	FLAKINESS	2.00%	8	SAND EQUIVALENT	>85%
2	GLASS CONTENT SION	15~22%	9	SIZE	0~100MM
3	K20 CONTENT	0.03%	10	SPECIFICATION	3.50%
4	LA ABRASION	19.00%	11	SULPHUR CONTENT	0.02%
5	NA20	0.13%	12	TOTAL FE CONTENT	12~26%
6	MOISTURE CONTENT	0.10%	13	WATER ABSORPTION	1.10%
7	PLASTICITY	0.10%			

