

WHEN YOU NEED TO BE SURE

ALUMINUM INGOT SPECIFICATION



www.sopelinc.com



info@jsopelinc.com



+82-10-3422-2885



202HO 101 DONG HANSHIN VILLAT 258-29 HOWON DONG UIJEONG BU SHI GYEONGGI DO SOUTH KOREA.



ALUMINUM INGOT SPECIFICATION

NO	ARTICLE	A0	A5	A5E	A6	A7	A7E	A7ᄇ	A8	A85
1	Al	99.00	99.50	99.50	99.60	99.70	99.70	99.70	99.80	99.85
2	CA	(----)	0.03	0.03	0.03	0.03	0.03	0.04	0.03	0.03
3	CU	0.05	0.02	0.02	0.01	0.01	0.01	0.01	0.01	0.01
4	FE	0.95	0.30	.35 ¹⁾	0.25	0.16	0.20	0.20	0.1	0.08
5	MG	0.05	0.03	0.03	0.03	0.02	0.02	(----)	0.02	0.02
6	MN	0.05	0.05	(----)	0.03	0.03	(----)	0.03	0.02	0.02
7	OTHER IMPURITIES	0.03	0.03	0.02	0.03	0.02	0.02	0.03	0.02	0.02
8	SI	0.95	0.25	0.10	0.18	0.15	0.08	0.10	0.10	0.06
9	TI	0.02	0.02	0.15 ³⁾	0.02	0.01	0.01 ³⁾	0.01 ³⁾	0.01	0.008
10	ZN	0.10	0.06	0.04	0.05	0.04	0.04	0.03	0.04	0.02

