

WHEN YOU NEED TO BE SURE

IRON ORE PELLETS



www.sopelinc.com



info@jsopelinc.com



+82-10-3422-2885



202HO 101 DONG HANSHIN VILLAT 258-29 HOWON DONG UIJEONG BU SHI GYEOUNGI DO SOUTH KOREA.

IRON ORE PELLETS

No	ELEMENT	RESULT
1	T.FE	65% MIN
2	FEO	1% MAX
3	AL2O3+SI02	5% MAX
4	P	0.01% MAX
5	S	0.01% AVE
6	MOISTURE	1% MAX
7	CCS	270KG/PELLET MIN
8	T INDEX	96% MIN
9	A INDEX	2% MAX
10	PROSITY	20-25%
11	SIZE 6.3 - 16 MM	90% MIN
12	SIZE +16 MM	1% MAX
13	SIZE<6.3 MM	2% MAX



IRON ORE PELLETS

+82-10-3422-2885

info@sopelinc.com

Jee Wan Kim Mr.

202HO 101 DONG HANSHIN VILLAT 258-29 HOWON DONG UIJEONG BU SHI GYEONGGI DO SOUTH KOREA.